



Great Industries Corp.

2021 Elm Court, Ontario, CA91761

Tel: (909) 930-6322 Fax: (909) 930-6326

Specification Sheet **(#7096 Rubber Base Pressure Sensitive)**

1. High temperature rubber base pressure sensitive adhesive
2. Aggressive - high tack

	Unit	Average	Unit	Average
Peel Adhesion (PSTC-1)	kg/cm	1.20	pound/inch	6.72
Holding Power (PSTC-7)	minute	250	minute	250
SAFT	°C	50	°F	120

PSTC-1 and PSTC-7 are the hot melt adhesive holding power and temperature test method.

Recommended Substrates:

ABS, Acrylic Sheet, Aluminum, Ceramic Tile,
Elpo Panel, Glass, Lacquered & Raw Plywood,
Polycarbonate, Polyester/Fiberglass,
Polyethylene, Polypropylene, Raw Steel, Rigid Vinyl

For the best results, we strongly suggest adhesive to be applied at a room temperature of 68 degree F or higher. Surface should be clean, dry and free of oils. Though our test indicates good peel adhesive to the listed substrates, but actual performance may vary due to grade of substrates. Therefore, we suggest you perform your own test.